

## **316L** Fe-based Alloy Powder for Additive Manufacturing 90/45 µm, Gas Atomized Designed for LMD

#### Chemical composition similar to DIN 1.4404, UNS S31603, X2CrNiMo17-12-2

#### **DESCRIPTION**

316L is a gas atomized stainless steel alloy powder engineerered for additive manufacturing (AM). This material is a low carbon austenitic stainless steel alloy comprising of chromium, nickel, and molydenum, providing superior corrosion resistance compared to 304L, while maintaining good mechanical properties.

This material has a wide range of applications across various industries due to its range of properties. It is well-suited for applications that require a combination of strength, ductility, and resistance to pitting and corrosion in harsh environments, therefore finding its place in many general engineering applications.

## **KEY PROPERTIES**

- High corrosion resistance
- Excellent ductility
- Resistance to pitting
- Resistance to corrosion, oxidizing, and reducing environments

#### **APPLICATIONS**

- Marine and naval components
- Pressure vessels and storage tanks
- Offshore oil and gas equipment
- Pulp and paper machinery
- General engineering applications

## **POWDER CHEMICAL COMPOSITION**

Element	Min. (wt%)	Max. (wt%)
Fe	Bal.	Bal.
Cr	16.0	18.0
Ni	10.0	14.0
Мо	2.0	3.0
Mn	-	2.0
Si	-	1.0
С	-	0.02

#### **SEM IMAGE**



#### POWDER PROPERTIES (ISO 4490, ISO 3923-1)

Particle Size	Hall Flow	Apparent Density
Distribution (µm)	(s/50g)	(g/cm <sup>3</sup> )
45 — 90	13.8	4.42

#### **MICROGRAPHS**



**Polished Surface** 

#### PHYSICAL PROPERTIES (ISO 3369)

Average Defect Percentage (%)	Density (g/cm³)
< 0.10	> 7.91



Microstructure

#### MECHANICAL PROPERTIES (ISO 6892-1)

Orientation	Ultimate Tensile Strength (MPa)	te Tensile 0.2% Yield gth (MPa) Strength (MPa)	
Horizontal	$666 \pm 6$	363 ± 12	34 ± 5
Vertical	607 ± 14	$269\pm4$	47 ± 1

#### HARDNESS (ISO 6507-1)

HV <sub>0.3</sub>	Celsius (°C)	Fahrenheit (°F)
	1371 - 1399	2500 - 2550

#### **PROCESS INFORMATION:**

The properties reported in this Technical Data Sheet are applicable to Makino AM powders tested and distributed by Makino and processed on Makino LMD machine utilizing parameters in accordance with relevant operating guidelines (inclusive of setup conditions and maintenance). The properties are obtained by following recommended protocols. Further information regarding the methods used by Makino can be provided upon inquiry.

**MELTING POINT** 

#### **DISCLAIMER:**

The data and information provided represent, to the best of our knowledge, standard or average values and do not constitute guarantees for upper and lower limit parameters. The recommended applications for the material disclosed are exclusively for illustrative purposes that help the reader to conduct their independent assessments. These suggestions are not intended to be expressed or implied warranties of suitability for the specified applications or any other purposes. The information included may be subject to change at any time without prior notification.

#### **CONTACT US:**

Our Safety Datasheet (SDS) is available upon request. For more information or support please contact Makino at sales-am@makino.com.sg or visit www.makino.com.sg

#### MA.101312.TDS2

©2024 Makino Asia Pte Ltd | All rights reserved



# **316L**

## Fe-based Alloy Powder 53/20 µm, Gas Atomized Designed for Additive Manufacturing, L-PBF

Chemical composition similar to DIN 1.4404, UNS S31603, X2CrNiMo17-12-2

#### **DESCRIPTION**

316L is a gas atomized stainless steel alloy powder engineerered for additive manufacturing (AM). This material is a low carbon austenitic stainless steel alloy comprising of chromium, nickel, and molydenum, providing superior corrosion resistance compared to 304L, while maintaining good mechanical properties.

This material has a wide range of applications across various industries due to its range of properties. It is well-suited for applications that require a combination of strength, ductility, and resistance to pitting and corrosion in harsh environments, therefore finding its place in many general engineering applications.

#### **KEY PROPERTIES**

- High corrosion resistance
- Excellent ductility
- Resistance to pitting
- Resistance to corrosion, oxidizing, and reducing environments

#### **APPLICATIONS**

- Marine and naval components
- Pressure vessels and storage tanks
- Offshore oil and gas equipment
- Pulp and paper machinery
- General engineering applications

#### **POWDER CHEMICAL COMPOSITION**

Element	Min. (wt%)	Max. (wt%)
Fe	Bal.	Bal.
Cr	16.0	18.0
Ni	10.0	14.0
Мо	2.0	3.0
Mn	-	2.0
Si	-	1.0
С	-	0.02

#### **SEM IMAGE**



## POWDER PROPERTIES (ISO 4490, ISO 3923-1)

Particle Size	Hall Flow	Apparent Density
Distribution (µm)	(s/50g)	(g/cm³)
20 - 53	17.6	4.25

## **MICROGRAPHS**



Polished Surface

Microstructure

### MECHANICAL PROPERTIES (ISO 6892-1)

Orientation	Ultimate Tensile Strength (MPa)	0.2% Yield Stress (MPa)	Elongation at break (%)
Horizontal	713 ± 6	653 ± 12	55 ± 5
Vertical	660 ± 14	613 ± 4	48 ± 1

## PHYSICAL PROPERTIES (ISO 3369)

## **MELTING POINT**

Average Defect Percentage (%)	Density (g/cm³)	Celsius (°C)	Fahrenheit (°F)
< 0.1	> 7.94	1371 - 1399	2500 - 2550

## HARDNESS (ISO 6507-1)

HV <sub>0.3</sub>	HRC
228	20

#### **SURFACE ROUGHNESS**



#### **PROCESS INFORMATION:**

The properties reported in this Technical Data Sheet are applicable to Makino AM powders tested and distributed by Makino and processed on Makino LMD machine utilizing parameters in accordance with relevant operating guidelines (inclusive of setup conditions and maintenance). The properties are obtained by following recommended protocols. Further information regarding the methods used by Makino can be provided upon inquiry.

#### **DISCLAIMER:**

The data and information provided represent, to the best of our knowledge, standard or average values and do not constitute guarantees for upper and lower limit parameters. The recommended applications for the material disclosed are exclusively for illustrative purposes that help the reader to conduct their independent assessments. These suggestions are not intended to be expressed or implied warranties of suitability for the specified applications or any other purposes. The information included may be subject to change at any time without prior notification.

#### **CONTACT US:**

Our Safety Datasheet (SDS) is available upon request. For more information or support please contact Makino at sales-am@makino.com.sg or visit www.makino.com.sg

#### MA.101312.TDS2 ©2024 Makino Asia Pte Ltd | All rights reserved